

Technical Data Sheet

TDS

General Description

Product Name	Permanent Yellow WSR
Epsilon Code	ECY06201
Color Index	Pigment Yellow 62
C.I. No.	13940
CAS	12286-66-7
EINECS NO.	235-558-4
Chemical Group	Monoazo Lake

Physical and Chemical properties

Test Items	Specification
Appearance	Reddish Yellow Powder
Acid Resistance	5
Alkali Resistance	5
Alcohol Resistance	5
Soap Resistance	5
Bleeding Resistance	---
Migration Resistance	5
BET Surface Area, m ² /g	---
Heat Resistance, °C	250
Light Fastness	6-7
Oil Absorption, g/100g	35-45
Moisture, %	1.5 max.
Water Soluble Matter, %	1.5 max.
Residue (120mesh), %	5.0 max.
PH Value	6.0-8.0

Application

Plastics, PVC, PP, PE rubbers.

Package

25kg bag or drum with pallets.

Hangzhou Epsilon Chemical Co.,Ltd.

T.: +86-571-82270817

F.: +86-571-82660715

E: info@epsilonpigments.com

W: <http://www.epsilonpigments.com>