

Technical Data Sheet**TDS****General Description**

Product Name	Light Chrome Yellow 401
Type	Yellow pigment
Delivery Form	Powder
Color Index	Pigment yellow 34 (77600)
CAS	1344-37-2
EINECS NO.	215-693-7

Physical and Chemical properties

Test Items	Specification
Appearance	Yellow powder
Shade	Greenish
Oil Absorption, %	22 max.
Residue (on 325mesh sieve), %	1.0 max.
Water Soluble, %	1.0 max.
Tinting Strength, %	95-105
PH Value	6.0-9.0
Heat Resistance, °C	180
Light Fastness	5-6
Weather Resistance	3-4
Acid Resistance	2-3
Alkali Resistance	2-3

Application

Light chrome yellow 401 is recommended to be used in paints and coatings, industrial paints, marine coatings, aviation coatings, architectural coatings, construction machinery coatings, shipping container coatings, plastics, functional master batches, artificial leather.

Package

25kg bag with pallets.

Hangzhou Epsilon Chemical Co.,Ltd.

T.: +86-571-82270817

F.: +86-571-82660715

E: info@epsilonpigments.com

W: <http://www.epsilonpigments.com>