

Technical Data Sheet**TDS****General Description**

Product Name	Medium Chrome Yellow E207
Type	Yellow pigment
Delivery Form	Powder
Color Index	Pigment yellow 34 (77600)
CAS	1344-37-2
EINECS NO.	215-693-7

Physical and Chemical properties

Test Items	Specification
Appearance	Yellow powder
Shade	Reddish
Oil Absorption, %	17 max.
Residue (on 325mesh sieve), %	1.0 max.
Water Soluble, %	1.0 max.
Tinting Strength, %	95-105
PH Value	5.4-7.0
Heat Resistance, °C	240
Light Fastness	6-7
Weather Resistance	3-4
Acid Resistance	3
Alkali Resistance	2

Application

Paints and coatings, industrial paints, coil coatings, marine coatings, aviation coatings, automotive OEM and re-finish paints, architectural coatings, construction machinery coatings, shipping container coatings, thermoplastic road marking paints, traffic coatings, fluorocarbon coatings, heat-resistant coatings, plastics, functional master batches, artificial leather.

Package

25kg bag with pallets.

Hangzhou Epsilon Chemical Co.,Ltd.

T.: +86-571-82270817

F.: +86-571-82660715

E: info@epsilonpigments.com

W: <http://www.epsilonpigments.com>