

**Technical Data Sheet****TDS****General Description**

Product Name	Orange Chrome Yellow E906
Type	Yellow pigment
Delivery Form	Powder
Color Index	Pigment yellow 34 (77600)
CAS	1344-37-2
EINECS NO.	215-693-7

**Physical and Chemical properties**

Test Items	Specification
Appearance	Yellow powder
Shade	Reddish
Oil Absorption, %	15 max.
Residue (on 325mesh sieve), %	1.0 max.
Water Soluble, %	1.0 max.
Tinting Strength, %	95-105
PH Value	5.0-8.0
Heat Resistance, °C	220
Light Fastness	7
Weather Resistance	5
Acid Resistance	5
Alkali Resistance	5

**Application**

High temperature paints and coatings, coil coatings, automotive OEM and re-finish paints, heat-resistant coatings, fluorocarbon coatings, high temperature plastics, functional master batches, artificial leather.

**Package**

25kg bag with pallets.

Hangzhou Epsilon Chemical Co.,Ltd.

T.: +86-571-82270817

F.: +86-571-82660715

E: [info@epsilonpigments.com](mailto:info@epsilonpigments.com)

W: <http://www.epsilonpigments.com>